



VeroClear

RIGID TRANSPARENT POLYJET MATERIAL

VeroClear™, a transparent PolyJet™ photopolymer, offers strength, stiffness and impact resistance ideal for concept modeling, design verification and functional testing of clear parts. VeroClear simulates PMMA (polymethyl methacrylate), commonly known as acrylic, and enables the visualization of internal components and features ideal for form and fit testing of see-through parts such as eyewear, light covers and medical devices. 3D print transparent parts, or blend with other PolyJet materials for a range of opacities, stunning hues or hardnesses, a versatility ideal for rapid prototyping. To achieve the best clarity, parts should be polished, lacquered or photo bleached.



TO LEARN MORE ABOUT VEROCLEAR, VISIT

[STRATASYS.COM](https://www.stratasys.com)



VeroClear

RIGID TRANSPARENT POLYJET MATERIAL

At the core:

PolyJet Technology

PolyJet technology creates precise prototypes that set the standard for finished-product realism. Their fine resolution makes complex shapes, intricate details and smooth surfaces possible. PolyJet 3D Printing works by jetting layers of liquid photopolymer onto a build tray and instantly curing them with UV light. The fine layers build up to create a precise 3D model or prototype. Models are ready to handle right out of the 3D printer, with no post-curing needed.

Keep valuable

resources in-house

You'll be amazed when you see how easy it is to produce realistic models in-house. PolyJet 3D Printers offer not only unparalleled speed, they make it easy for you to print with the widest range of material properties.

No special facilities needed

You can install PolyJet 3D Printers just about anywhere. No special venting is required because PolyJet 3D Printers don't produce noxious fumes, chemicals or waste.

Good ideas sell easier

PolyJet 3D Printers improve communication and collaboration because they produce amazingly accurate representations of your ideas that you can share with your team and your clients for a faster, more confident buy-in.

	ASTM	METRIC	ENGLISH
Tensile Strength	D-638-03	50-65 MPa	7,250-9,450 psi
Elongation at Break	D-638-05	10-25%	10-25%
Modulus of Elasticity	D-638-04	2,000-3,000 MPa	290,000-435,000 psi
Flexural Strength	D-790-03	75-110 MPa	11,000-16,000 psi
Flexural Modulus	D-790-04	2,200-3,200 MPa	320,000-465,000 psi
HDT, °C @ 0.45MPa	D-648-06	45-50 °C	113-122 °F
HDT, °C @ 1.82MPa	D-648-07	45-50 °C	113-122 °F
Izod Notched Impact	D-256-06	20-30 J/m	0.375-0.562 ft-lb/inch
Water Absorption	D-570-98 24hr	1.1-1.5%	1.1-1.5%
Tg	DMA, E _∞	52-54 °C	126-129 °F
Shore Hardness (D)	Scale D	83-86	83-86
Rockwell Hardness	Scale M	73-76	73-76
Polymerized Density	ASTM D792	1.18-1.19 g/cm ³	
Ash Content	USP281	0.02-0.06%	0.02-0.06%

SYSTEM AVAILABILITY	MINIMUM LAYER THICKNESS	SUPPORT STRUCTURE	AVAILABLE COLORS
Objet30 Pro™ Objet30 Prime™ Objet Eden260VS™ Objet260/500 Connex1™ Objet260/350/500 Connex3™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706 (soluble)	Clear
Stratasys J735™/J750™	14 microns (0.00055 in.)		
Objet1000 Plus™	16 microns (0.0006 in.)		

PIXEL SISTEMAS

www.pixelsistemas.com

Pol. Ind. SIGMA. Xixilion 2 · 2º
20870 ELGOIBAR (Gipuzkoa)

tel.: (+34) 943 74 86 02
marketing@pixelsistemas.com

stratasys

STRATASYS.COM

ISO 9001:2008 Certified

HEADQUARTERS

7665 Commerce Way,
Eden Prairie, MN 55344
+1 800 801 6491 (US Toll Free)
+1 952 937 3000 (Intl)
+1 952 937 0070 (Fax)

1 Holtzman St., Science Park,
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

© 2018 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Vero, VeroClear, Objet30 Pro, Objet30 Prime, Objet260 Connex1, Objet500 Connex1, Objet Eden260VS, Objet260 Connex3, Objet350 Connex3, Objet500 Connex3, Stratasys J735, Stratasys J750, Objet1000 Plus and PolyJet are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. Printed in the USA. MSS_PJ_VeroClear_A4_0318a