



Tango

POLYJET SIMULATED RUBBER MATERIAL

Flexible Tango™ material exhibits rubber-like qualities to simulate soft-touch coatings, non-slip surfaces, overmolding grips, shoe soles and other applications requiring flexible characteristics. Tango material is available in black, gray and translucent colors, and in a range of Shore A hardness values comparable to rubber bands, tire treads and shoe heels.



TO LEARN MORE ABOUT TANGO VISIT [STRATASYS.COM](https://www.stratasys.com)



Tango

POLYJET SIMULATED RUBBER MATERIAL

At the core: PolyJet™ Technology

PolyJet technology creates precise prototypes that set the standard for finished-product realism. Their fine resolution makes complex shapes, intricate details and smooth surfaces possible. PolyJet 3D Printing works by jetting layers of liquid photopolymer onto a build tray and instantly curing them with UV light. The fine layers build up to create a precise 3D model or prototype. Models are ready to handle right out of the 3D printer, with no post curing needed.

Keep valuable resources in-house

You'll be amazed when you see how easy it is to produce realistic models in-house. PolyJet 3D Printers offer not only unparalleled speed, they make it easy for you to print with the widest range of material properties.

No special facilities needed

You can install PolyJet 3D Printers just about anywhere. No special venting is required because PolyJet 3D Printers don't produce noxious fumes, chemicals or waste.

Good ideas sell easier

PolyJet 3D Printers improve communication and collaboration because they produce amazingly accurate representations of your ideas that you can share with your team and your clients for a faster, more confident buy-in.

TangoBlackPlus FLX980 and TangoPlus FLX930

	ASTM	METRIC	ENGLISH
Tensile Strength	D-412	0.8-1.5 MPa	115-220 psi
Elongation at Break	D-412	170-220%	170-220%
Compressive Set	D-395	4-5%	4-5%
Shore Hardness (A)	D-2240	26-28 Scale A	26-28 Scale A
Tensile Tear Resistance	D-624	2-4 Kg/cm	18-22 lb/in
Polymerized Density	D-792	1.12-1.13 g/cm ³	

TangoBlack FLX973

	ASTM	METRIC	ENGLISH
Tensile Strength	D-412	1.8-2.4 MPa	115-220 psi
Elongation at Break	D-412	45-55%	45-55%
Compressive Set	D-395	0.5-1.5%	0.5-1.5%
Shore Hardness (A)	D-2240	60-62 Scale A	60-62 Scale A
Tensile Tear Resistance	D-624	3-5 Kg/cm	18-24 lb/in
Polymerized Density	D-792	1.14-1.15 g/cm ³	

TangoGray FLX950

	ASTM	METRIC	ENGLISH
Tensile Strength	D-412	3-5 MPa	435-725 psi
Elongation at Break	D-412	45-55%	45-55%
Compressive Set	D-395	0.5-1.5%	0.5-1.5%
Shore Hardness (A)	D-2240	73-77 Scale A	73-77 Scale A
Tensile Tear Resistance	D-624	8-12 Kg/cm	50-60 lb/in
Polymerized Density	D-792	1.16-1.17 g/cm ³	

SYSTEM AVAILABILITY	LAYER THICKNESS CAPABILITY	SUPPORT STRUCTURE	AVAILABLE COLORS
Objet30 Prime™	28 microns	SUP705 (WaterJet removable) SUP706 (Soluble)	Black, Gray
Objet260/500 Connex1™	16 microns	SUP705 (WaterJet removable) SUP706 (Soluble)	Black, Gray, Translucent
Objet260/350/500 Connex3™	16 microns		Black, Gray, Translucent
Stratasys J735™, Stratasys J750™	14 microns		Black, Gray, Translucent
Objet1000 Plus™	16 microns	SUP705 (WaterJet removable)	Black, Translucent

stratasys

STRATASYS.COM
ISO 9001:2008 Certified

HEADQUARTERS
7665 Commerce Way,
Eden Prairie, MN 55344
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

PIXEL SISTEMAS

www.pixelsistemas.com

Pol. Ind. SIGMA. Xixilion 2 · 2º
20870 ELGOIBAR (Gipuzkoa)

tel.: (+34) 943 74 86 02
marketing@pixelsistemas.com

©2018 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, PolyJet, Objet, Objet30 Prime, Objet Eden260VS, Connex, Objet260 Connex1, Objet500 Connex1, Objet260 Connex3, Objet350 Connex3, Objet500 Connex3, Stratasys J735, Stratasys J750, Objet1000 Plus, Tango, TangoPlus, TangoBlack, TangoBlackPlus and TangoGray are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. Printed in the USA. MSS_PJ_Tango_0318a